

Water
CrystalPoint™
UV Curable
Latex

Coated Papers

IJM123(C) Premium Paper - FSC®

130 g/m²

Product Description

IJM123(C) Premium paper is a high-quality matt coated paper for presentation quality CAD and GIS drawings with solid colour fills

Physical Properties

Weight	128 g/m ²	ISO 536	Brightness (D65)	>95%	ISO 2470-2
Thickness	150 µm	ISO 534	Tensile strength MD/CD	>6,5/3,5 kN/m	ISO 1924-1
Smoothness (Bekk)	100 s	ISO 5627	Tearing strength MD/CD	>900/900 mN	ISO 1974
Opacity	>90%	ISO 2471			

All values listed are target values

Applications/features

Colour and monochrome CAD and GIS
 High-quality standard and presentation drawings
 Presentation quality
 Excellent dot gain and line sharpness
 Good contrast,
 Good smear resistance

Available Widths (mm)

2" core (IJM123)	594	610	841	914	1067
3" core (IJM123C)	420			1000	

Refer to our current offering to www.canon-europe.com/mediaguide

Storage Conditions

Temperature 10-30°C, Relative Humidity 20-80%
 Repack opened rolls when not in use.

Print Conditions

Best results between 15°-25° C and 30-70% RH

Environment, Health & Safety

No Material Safety Data Sheet required
 Waste can be handled as paper waste

Lamination Compatibility

Cold	Warm	Hot	Cold: pressure sensitive Warm: heat activated: 85°C - 95°C Hot: heat activated: 105°C -130°C
yes	yes	no	

Outdoor Use

This material is not suitable for outdoor use.

Colour Profiles

Canon develops high-quality colour profiles for media / ink / printer / RIP combinations.
 Check availability of profiles for your printer on www.canon-europe.com/mediaguide

Environmental Certification



Processing Guidelines

Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing. Side to be printed is the outer side of the roll.

Make sure that the media comes not into contact with grease, oil, silicon, and dirt to avoid printing defects. It is recommended to handle the media with cotton gloves.

Insert the paper with care in the printer. Incorrect loading can cause skewing or creasing. It is recommended to calibrate the printer before printing and to make a test print.

Print results will vary for different printer ink combinations. Ink restrictions and printer settings should be set for specific printer-ink combinations to obtain the best results.

Canon media profiles include optimal ink and printer settings for Canon supported printers. Depending on fluctuations in environment, printer, ink, media and applications, printer parameters may have to be adjusted slightly, to obtain the best results.

Too much ink will cause paper cockle and possible head strikes. The use of dye inks can lead to premature fading of colors.

Application guidelines

The use of cold or warm laminates are recommended for the best results.

Allow the print to dry properly before to lamination. That is at least 24 hours. Too much ink can cause cockling which can cause problems with laminating.

For mounting on a board, an encapsulating edge of 5-6mm around the image is recommended. This prevents against moisture and paper splitting because of the tension of the laminate. One sided lamination may cause curling. Use laminates of equal gauge when encapsulating to prevent image curl.

Generally, lamination will only slightly improve UV resistance (pigmented inks should be used when UV resistance is required).

Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.